

# Acroprime

## Pink Wood Primer

 acro paints



ACROPRIME PINK WOOD PRIMER is an economy primer formulated with high quality resins and special pigments for the protection of wood and better performance of the finishing coats. It also ensures excellent adhesion, high degree of wood filling and wood sealing properties.

### PRODUCT BENEFITS



### PRODUCT FEATURES

#### AREAS OF APPLICATION




Wood

#### FINISH

- SMOOTH ✓
- MATT ✓

#### PACKAGING AVAILABLE



Shelf Life: 18 months from date of manufacturing in original tightly closed containers away from direct sunlight and excess heat.

#### COVERAGE

On normal wood surface by Brush / Spray



8 - 10  
sq. mtr. / ltr. / coat\*

\*Actual Coverage will vary according to the porosity and texture of the surface. However, on moderately smooth surface

#### COLOURS AVAILABLE

**Pink\***



\*Acroprime Pink Wood Primer is an undercoat

### HOW TO APPLY

**SURFACE PREPARATION:** Ensure that the surface is free from dirt, dust, oil, moisture, grease, loose particles etc.

**APPLICATION:** Apply 1-2 coats of Pink Wood Primer for best results on a properly prepared surface. An interval of 8 hrs. should be given in case of giving two coats.

## PAINT APPLICATION PROCESS

APPLICATION	THINNER	DILUTION % (BY VOLUME)	APPLICATION <sup>1</sup> VISCOSITY(SEC)	RECOATING PERIOD <sup>2</sup> (HOURS)
<b>STEP 1 SANDING</b>				
<b>SAND LIGHTLY WITH SAND PAPER 180 AND WIPE CLEAN</b>				
STEP 2 FIRST COAT ACROPRIME PINK WOOD PRIMER BRUSH / ROLLER / SPRAY	 MTO	BRUSH 8 - 10 SPRAY 13 - 15	40 - 45 SEC	8 - 12 Hrs.
<b>STEP 3 SANDING</b>				
<b>SAND LIGHTLY WITH SAND PAPER 180 AND WIPE CLEAN</b>				
STEP 4 SECOND COAT ACROPRIME PINK WOOD PRIMER BRUSH / ROLLER / SPRAY	 MTO	BRUSH 8 - 10 SPRAY 13 - 15	40 - 45 SEC	8 - 12 Hrs.

1. As measured through a Ford cup.

2. Recoating period is quoted for 25°C and 50% Relative Humidity, these may vary under different conditions.

## TECHNICAL DETAILS

**a. Drying time :** Surface dry time 30 min.

**b. Flash point IS101/1987 Part 1, Sec 6:** > 30°C [ > 85° F ]

**c. Stability of thinned paint:** To be used within 24 hours

## PRECAUTIONS

Keep away from heat & flame. Close the container properly after use. Wash the equipment with mineral turpentine oil immediately after use.

## SAFETY FEATURES

- ❖ Kindly refer to the MSDS for Acroprime Pink Wood Primer which gives detailed information on safety measures while handling the paint.
- ❖ Store the container with the lid tightly closed in an upright position, in a cool, dry place.
- ❖ Keep out of reach of children and away from food, drink etc.
- ❖ May be harmful, if swallowed. In case of ingestion, seek immediate medical attention.
- ❖ Wear eye protection during application. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- ❖ In case of skin contact immediately wash skin with soap and plenty of water. Get medical attention if irritation develops or persists.
- ❖ Do not breathe vapour or spray. It is recommended to wear suitable nose pad during sanding and surface preparation to avoid dust inhalation.
- ❖ Do not pour leftover paint down the drain or in water courses.
- ❖ In the event of spills, contain spillage using sand or earth.
- ❖ Safety Data Sheet available for professional user on request.
- ❖ No added Lead, Mercury or Chromium compounds.